

BARRWELD™ FABRIC SPECIFICATIONS



		Barrweld™
Content		Lenzing™ FR / Twaron® Blend
Weight		8.5 oz (sq yd)
Finish		None
Abrasion	ASTM D3884-22	430 Level 1
Thermal Shrinkage (%) warp x weft Ignition Deformation Degradation (and discoloration from wine color to light greenish/brown) Delamination Flaking Hole formation Separation Splitting	ASTM F2894-21	2.4 x 1.4 none none yes none none none none none none
Fabric Break Strength (Grab) (lbf) warp x weft	ASTM D5034-21	269.8 x 183.7
Tearing Strength (Trapezoid) (lbf) warp x weft	ASTM D5587-15	36.1 x 22.2
Vertical Flame After flame (sec) warp x weft Char length (mm) warp x weft	STM D6413M-15	.1 x .1 15 x 11
Melt/Dripping?	ASTM D6413M-15	None
Cut Rating Grams	ASTM F2992-15	N/A Level A1
ArcFlash ATPV – cal/cm²	ASTM 1959	6.9 – HRC1

Tri-Star Glove believes in offering excellent value by delivering domestically produced, high-quality hand and body protection in a timely manner.

Disclaimer: The data presented herein has been developed under controlled manufacturing conditions is considered accurate. No warranty is expressed or implied regarding the accuracy or use of this data or the use of these products. It is the responsibility of the end user to determine suitability for use.